2025/11/01 14:48 1/4 Cricut Maker Training SOP

Cricut Maker Training SOP

Last edited: Furst (10/08/20)

Instructor:

Date:

Attendees:

Name Group or Company Signature

1
2
3
4
5

Overview:

- This training provides an introduction to using and operating the Cricut Maker including:
 - File Types
 - Software
 - Cricut Use
 - Cricut Maintenance
 - Changing cutting Heads
 - Cleaning
- The Cricut is currently set up in the window sill of 2448 and is attached to the Carbide computer
- Work by cutting a thin part in plane to create complex 2D shapes in a repeatable and precise manner.

Safety

- The cutting heads are very sharp, caution should be taken whenever replacing or switching out the Cricut cutting head
- As with any automated machinery make sure that your body is clear of the moving parts to avoid injury.

Job Setup

1. At the Computer::

- 1. Load your STL file into the print software on the computer adjacent to the printer (Cura for Ultimaker, GrabCad Print for F270).
- 2. Set Print Parameters:
 - 1. Position the part on the build tray in a way that is conducive to 3D printing (flat side down)
 - 2. Select appropriate layer or slice height (the more slices the higher the print

resolution but the longer it takes to print)

- 3. For Ultimaker:
 - 1. Select "generate support" if necessary
 - 2. Check appropriate filament and bed temperatures (should be set if using standard filament load out)
 - 3. Send job to Ultimaker using USB drive
- 4. For F270:
 - 1. The F270 the printer will print a raft before printing the model. Make sure first layer is set to support material or removal will be incredibly difficult.
 - 2. Send job to F270 over Ethernet
- Record the material used and print time in the online log along with the other job information requested. The print log should be on the desktop or https://docs.google.com/forms/d/e/1FAIpQLScS3URUxoHOR62PdQeeSTAYg_suV061UsoFaf rgoN0qn6DWYg/viewform.

2. At the printer:

- 1. Ultimaker:
 - 1. Make sure print bed is clean
- 2. F270:
 - Make sure that there is enough room on an CLEAN build tray for your part, and that
 the build tray is secured in the printer with the locking arm horizontal. Build trays
 may be used until the entire build area has been printed on, but printed areas
 should ideally not be reused.
- 3. Start the job at the printer

Part Removal and Cleaning

Ultimaker

- Remove part from print bed using a spatula or razor being careful not to cut yourself or scratch
 the build plate. Make sure no body part is in line with the tool should it slip or the part break
 free unexpectedly.
- If support was used, submerge print in warm water for several hours to dissolve PVA filament. (prints can warp if submerged in water for over 24 hours)

F270

- Don gloves, face shield, and lab coat
- Carefully, slowly and without splashing cleaning solution open the support removal tank lid, remove and open the tank
- Place large parts directly in the tank, small parts may be put in the SS box and placed into the main basket.
- Carefully, slowly and without splashing lower the basket back into the tank and close the lid.
- Set timer for 6 hours setting the temperature to 80 degrees C.
- After cleaning time has elapsed follow the instructions above for opening and removing parts.
- Rinse part in warm water

Rates

2025/11/01 14:48 3/4 Cricut Maker Training SOP

F270:

Material	\$/Spool	cu in/Spool	\$/cu in	\$/cc
PLA	79	60	1.31	.08
ABS	164	60	2.73	.17
Sup	228	60	3.79	.23

F270 hourly charge: \$1/hr to pay for head replacement

Ultimaker: ABS: .12/gram

Ultimaker 3 Quick Review

Tool Lead: Andrew Furst

Contact: Andrewfurst@ucsb.edu

Safety Concerns

- Both print heads and bed are heated during operation. Do not attempt to clean, remove, or adjust without allowing for adequate cool down time.
- Keep hands clear of printer during operation. Pause print before clearing or adjusting print.

Safe Operating Procedures Review

- 1. Launch Cura version 4 (blue icon)
- 2. From connected printers, select IW-Ultimaker3
- 3. Select File → Open Files → Open desired project (.STL file type)
- 4. Using task bar on the left hand side, position model as desired
- 5. From print settings, select slice height, infill percentage, and support
- 6. Support can be generated using ether nozzle, typically nozzle one holds build material with nozzle two printing with dissolvable support material.
- 7. Setting can be fined tuned using the "Custom" option from print settings
- 8. Within custom settings, nozzle and build plate temps can be adjusted (build plate temps should be based off of build material)
- 9. Save the file from Cura on a thumb drive
- 10. Connect thumb drive to printer → select desired file → select print

Note: Adjusting settings may lead to more (OR LESS) successful prints. Contact Workshop Wizard responsible for Ultimaker if print fails or knowledge of advanced settings is desired.

Post Processing

- If support was constructed from ABS carefully break away with pliers
- If support was constructed from PVA soak part in warm water for several hours to dissolve

Last update: 2020/10/08 18:17

support structure

Maintenance

- Bed should be cleaned with IPA between prints
- Print heads and silicone head protector should be cleaned as needed
- Filament should be dried before use if printer has been idle for several weeks
- Bed leveling should be completed every time print cores are swapped
- Print cores should be swapped or purged after clog or to change print line width. Used print heads should be kept for spare parts

From:

https://bpm-wiki.cnsi.ucsb.edu/ - NSF BioPACIFIC MIP Wiki

Permanent link:

https://bpm-wiki.cnsi.ucsb.edu/doku.php?id=cricut_sop&rev=1602181032

Last update: **2020/10/08 18:17**

