

Ultimaker3 Extended Dual FDM 3D Printer



Ultimaker3 Extended Dual FDM 3D Printer	
Tool Type: "FDM 3D printer"	
Location: "CNSI Innovations Workshop"	
Supervisor	Tool Lead
David Bothman	Andrew Furst
(805) 893-4125	(801) 928-8869
bothman@cnsi.ucsb.edu	Andrewfurst@ucsb.edu
Description: "FDM 3D Printer"	
Manufacturer: "Ultimaker"	

About

The Ultimaker 3 extended is a filament fed fusion deposition 3D printer capable of simultaneously printing two different plastics at once. Typically the printer is set up with ABS as a build material, and PVA as a solvable support material.

Detailed Specifications

Build Volume: 215 x 215 x 300 mm

Filament diameter: 2.85 mm

layer resolution: 60 to 600 microns depending on print head (see Specifications documentation page 11)

XYZ accuracy: 12.5, 12.5, 2.5 microns

Build plate temperature: 20-100 °C

Nozzle temperature: 80 - 100 °C

Safety Concerns

Insert Text Here!

Operating Procedures

1. Launch Cura version 4 (blue icon)
2. From connected printers, select IW-Ultimaker3
3. Select File → Open Files → Open desired project (.STL file type)
4. Using task bar on the left hand side, position model as desired
5. From print settings, select slice height, infill percentage, and support
6. Support can be generated using ether nozzle, typically nozzle one holds build material with nozzle two printing with dissolvable support material.
7. Setting can be fined tuned using the “Custom” option from print settings
8. Within custom settings, nozzle and build plate temps can be adjusted (build plate temps should be based off of build material)
9. Save the file from Cura on a thumb drive
10. Connect thumb drive to printer → select desired file → select print

Note: Adjusting settings may lead to more (OR LESS) successful prints. Contact Workshop Wizard responsible for Ultimaker if print fails or knowledge of advanced settings is desired.

Reference Documentation

PVA Temps

Extruder: 220 C Bed: Whatever structural filament recommends

ABS Temps

Extruder: 230 C Bed: 100 C

[quick_start_guide_ultimaker_3_v3.2.pdf](#)

[ultimaker_3_extended_specifications.pdf](#)

[um180129_ultimaker_3_manual_rb_v12_english.pdf](#)

<https://support.ultimaker.com/hc/en-us/articles/360012007119>

[pva_drying_recipe.pdf](#)

[ultimaker_filaments_-_sheet1.pdf](#)

Training Documentation

[failed_3d_print_procedure.pdf](#)

From:

<https://bpm-wiki.cnsi.ucsb.edu/> - NSF BioPACIFIC MIP Wiki

Permanent link:

https://bpm-wiki.cnsi.ucsb.edu/doku.php?id=ultimaker3_extended&rev=1594753473

Last update: **2020/07/14 19:04**

