## **Ultimaker3 Extended Dual FDM 3D Printer**



**Ultimaker3 Extended Dual FDM 3D Printer** 

Tool Type: "FDM 3D printer"

**Location:** "CNSI Innovations Workshop"

	•
Supervisor	Tool Lead
David Bothman	Andrew Furst
(805) 893-4125	(801) 928-8869
bothman@cnsi.ucsb.edu	Andrewfurst@ucsb.edu

**Description:** "FDM 3D Printer" **Manufacturer:** "Ultimaker"

#### **About**

The Ultimaker 3 extended is a filament fed fusion deposition 3D printer capable of simultaneously printing two different plastics at once. Typically the printer is set up with ABS as a build material, and PVA as a solvable support material.

## **Detailed Specifications**

Build Volume: 215 x 215 x 300 mm Filament diameter: 2.85 mm

layer resolution: 60 to 600 microns depending on print head (see Specifications documentation page

11)

XYZ accuracy: 12.5, 12.5, 2.5 microns Build plate temperature: 20-100 °C Nozzle temperature: 80 - 100 °C

#### **Safety Concerns**

Insert Text Here!

### **Operating Procedures**

- 1. Launch Cura version 4 (blue icon)
- 2. From connected printers, select IW-Ultimaker3
- Select File → Open Files → Open desired project (.STL file type)
- 4. Using task bar on the left hand side, position model as desired
- 5. From print settings, select slice height, infill percentage, and support
- 6. Support can be generated using ether nozzle, typically nozzle one holds build material with nozzle two printing with dissolvable support material.
- 7. Setting can be fined tuned using the "Custom" option from print settings
- 8. Within custom settings, nozzle and build plate temps can be adjusted (build plate temps should be based off of build material)
- 9. Save the file from Cura on a thumb drive
- 10. Connect thumb drive to printer → select desired file → select print

Note: Adjusting settings may lead to more (OR LESS) successful prints. Contact Workshop Wizard responsible for Ultimaker if print fails or knowledge of advanced settings is desired.

### **Reference Documentation**

**PVA Temps** 

Extruder: 220 C Bed: Whatever structural filament recommends

**ABS Temps** 

Extruder: 230 C Bed: 100 C

quick\_start\_guide\_ultimaker\_3\_v3.2.pdf ultimaker\_3\_extended\_specifications.pdf um180129\_ultimaker\_3\_manual\_rb\_v12\_english.pdf https://support.ultimaker.com/hc/en-us/articles/360012007119 pva\_drying\_recipe.pdf ultimaker\_filaments\_- sheet1.pdf

# **Training Documentation**

FDM Printer SOP failed\_3d\_print\_procedure.pdf

From:

https://bpm-wiki.cnsi.ucsb.edu/ - NSF BioPACIFIC MIP Wiki

Permanent link:



