2025/07/02 12:41 1/2 FormCure UV Curing Station

# FormCure UV Curing Station

FormCure UV Curing Station
×
Tool Type: "UV Curing Station"
Location: "Innovations Worship"

Supervisor	Tool Lead
David Bothman	"WW Name"
(805) 893-4125	(###) ###-###
bothman@cnsi.ucsb.edu	"WW Email"

**Description:** "FormLabs Curing Station" **Manufacturer:** "FormLabs"

#### **About**

Some FormLabs Resins used in the Form 2 3D printer can benefit from post process curing. Each resin has a specific hardening curve which can be found within the reference material which will indicate the ideal time and temperature to be set on the FormCure.

#### **Detailed Specifications**

Max cure temp: 80 degrees C

• Light: 39W total drawn by 13 405 nm LEDs

#### **Safety Concerns**

- Allow at least half an hour for IPA to evaporate before placing part in Form Cure
- Allow time for the Form Cure to cool off before removing parts
- Do not operate form cure with lid open

### **Operating Procedures**

- 1. Any part to be cured needs to be washed in the FormWash with IPA BEFORE being placed in the form cure. Supports can be removed before or after curing process.
- 2. Wait 30 minutes after washing to allow all remaining IPA to evaporate
- Check the reference material for selected resin to determine ideal time and temperature for curing
- 4. Use the dial on the front of the FormCure to set time and temperature

5. Place part within the FormCure→ press start.

\_\_-

#### **Reference Documentation**

https://support.formlabs.com/s/article/Using-Form-Cure?language=en\_US

https://support.formlabs.com/s/article/Form-Cure-Time-and-Temperature-Settings?language=en\_US

https://support.formlabs.com/s/article/Form-Cure-Time-and-Temperature-Settings?language=en\_US

## **Training Documentation**

Insert Text Here!

From:

https://bpm-wiki.cnsi.ucsb.edu/dokuwiki/ - NSF BioPACIFIC MIP Wiki

Permanent link:

https://bpm-wiki.cnsi.ucsb.edu/dokuwiki/doku.php?id=formcure\_uv&rev=1602176355

Last update: 2020/10/08 16:59

