

Notes on preparing a MiiCraft PDMS mold for casting

Via Nate Jones – 11 Feb. 2020

**Cleaning**

IPA for 5min

**Curing**

600s under UV light

2h on the oven at 130C

Clean the surface with nitrogen gun

Silane treatment

Pour PDMS

Cure PDMS on the oven at 65C for 4h